

---

# TEST REPORT

APPLICANT : SHIWOO INTERNATIONAL

REPORT NO. : H216-10-00849

SAMPLE RECEIVED DATE : 2010-03-02

TEST STARTED DATE : 2010-03-02

REPORT ISSUED DATE : 2010-03-03

PAGE : 1 OF 2

SAMPLE DESCRIPTION : ONE(1) PIECE OF SUBMITTED CUTTING SAID TO BE RETRO-REFLECTIVE MATERIALS WHITE.

---

TEST CONDUCTED : AS REQUESTED BY THE APPLICANT, FOR DETAILS PLEASE SEE ATTACHED PAGE.

---

PREPARED AND CHECKED BY  
FOR FITI

AUTHORIZED BY  
FOR FITI

QUALITY MANAGER

EXECUTIVE DIRECTOR

TEST CONDUCTED

TEST RESULT

(01) COEFFICIENT OF RETROREFLECTION ( ASTM D 4956:2009 ) : cd/Lux.m<sup>2</sup>

OBSERVATION ANGLE(° )	ENTRANCE ANGLE(° )	COEFFICIENT OF RETROREFLECTION (cd/Lux.m <sup>2</sup> )
0.2	-4	46.8
	30	20.0
0.5	-4	58.1
	30	9.2

SAMPLE :