

TEST REPORT

APPLICANT : ANY LITE

REPORT NO. : H241-13-13139

SAMPLE RECEIVED DATE : 2013-08-29

TEST STARTED DATE : 2013-08-29

REPORT ISSUED DATE : 2013-09-04

PAGE : 1 OF 2

SAMPLE DESCRIPTION : ONE(1) PIECE OF SUBMITTED CUTTING SAID TO BE REFLECTIVE FABRIC.

ITEM : M-4000 REFLECTIVE T/C

TEST CONDUCTED : AS REQUESTED BY THE APPLICANT, FOR DETAILS PLEASE SEE ATTACHED PAGES.

PREPARED AND CHECKED BY
FOR FITI



YOUNG-MIN JEON
QUALITY MANAGER

AUTHORIZED BY
FOR FITI



MOON-OK NOH
PRESIDENT

※ Report Verification No.: DE73-7U5H-J6N2 ※

(You can see the authenticity of your test report through the above "Report Verification No." at FITI homepage.)

e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI.

REPORT NO. : H241-13-13139

PAGE : 2 OF 2

TEST CONDUCTED
TEST RESULT

(01) COEFFICIENT OF RETROREFLECTION (EN 471 : 2003) : cd/Lux.m²

OBSERVATION ANGLE		ENTRANCE ANGLE	COEFFICIENT OF RETROREFLECTION
			#1
$\varepsilon = 0^\circ$	12'	5°	493.9
		20°	508.1
		30°	462.1
		40°	287.6
	20'	5°	307.5
		20°	310.7
		30°	302.0
		40°	227.3
	1°	5°	34.7
		20°	39.8
		30°	40.5
		40°	32.6
	1° 30'	5°	16.0
		20°	14.5
		30°	12.7
		40°	13.1

NORE) TEST WAS CONDUCTED ONLY $\varepsilon = 0^\circ$ DIRECTION BY THE CLIENT'S REQUEST.

e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI.