

TEST REPORT



APPLICANT : KOLIGHT & CANA CO., LTD.

REPORT NO. : H240-15-22729

SAMPLE RECEIVED DATE : 2015-12-02

TEST STARTED DATE : 2015-12-02

REPORT ISSUED DATE : 2015-12-15

PAGE : 1 OF 2

DESCRIPTION : ONE(1) PIECE OF SUBMITTED CUTTING SAID TO BE FABRIC.

=====

ITEM : STORED LIGHT

=====

TEST CONDUCTED : AS REQUESTED BY THE APPLICANT, FOR DETAILS PLEASE SEE ATTACHED PAGES.

=====

PREPARED AND CHECKED
FOR FITI



JONG-BUM KIM
QUALITY MANAGER

AUTHORIZED BY
FOR FITI



MOON-OK NOH
PRESIDENT

※ Report Verification No.: LY8K-1G68-1QUX ※

(You can see the authenticity of your test report through the above "Report Verification No." at FITI homepage.)

e-DOCUMENT SERVICE

The test results contained in this report are limited to results on the sample(s) that is provided by client and are not necessarily indicative or representative of the qualities of the lot from which the sample(s) was taken or of all products. Results contained in this report are not based on the quality certification of sample by the FITI quality certification program unless specifically requested by the client. Further use of the results of this report is prohibited unless allowed under a separate agreement set forth in an official document that is established between the client identified on this letter and the FITI. This test report is irrelevant to KOLAS accreditation.

01. PHOSPHORESCENT LUMINANCE (CLIENT'S REQUEST METHOD) : mcd/m²

	#1
ELAPSE TIME	
AS RECEIVED	
- 5 min	651.9
- 10 min	356.9
- 20 min	188.8
- 60 min	60.0
AFTER THE 15TH WASHING	
- 5 min	605.0
- 10 min	311.3
- 20 min	163.8
- 60 min	45.0

NOTE) MEASUREMENT DISTANCE : 0.25 m

MEASUREMENT AREA : 100.0 cm²

SOURCE IRRADIATION : SUNLIGHT EXPOSURE, 15 min

TEST LOCATION : 21, YANGCHEONG-3GIL, OCHANG-EUP CHEONGWON-GU, CHEONGJU-SI, CHUNGBUK

TEST DATE AND TIME : 2015.12.16, 13 : 00

WASHING CONDITION : KS K ISO 6330 : 2011, 11B, (30 ± 3) °C, FLAT DRY

**** End of The Report ****

SAMPLE :