

## TEST REPORT

APPLICANT : KOLIGHT & CANA CO., LTD.

REPORT NO. : H211-11-00670

SAMPLE RECEIVED DATE : 2011-01-11

TEST STARTED DATE : 2011-01-11

REPORT ISSUED DATE : 2011-01-17

PAGE : 1 OF 2

SAMPLE DESCRIPTION : TWO(2) PIECES OF SUBMITTED CUTTING SAID TO BE WOVEN FABRIC.

ITEM : RAIN COAT

TEST CONDUCTED : AS REQUESTED BY THE APPLICANT, FOR DETAILS PLEASE SEE ATTACHED PAGES.

PREPARED AND CHECKED BY  
FOR FITI

Young Ki Lee

YOUNG KI, LEE  
QUALITY MANAGER

AUTHORIZED BY  
FOR FITI

Moon Ok Noh

MOON-OK NOH  
EXECUTIVE DIRECTOR

TEST CONDUCTED

TEST RESULT

(01) FIBER COMPOSITION ( KS K 0210:2007 ) : %

	#1	#2
NYLON	100	100

(02) TEARING STRENGTH ( KS K ISO 13937-1:2009, PENDULUM METHOD ) : N

	#1	#2
WARP	6.6	4.9
WEFT	5.2	3.8

(03) AIR PERMEABILITY ( KS K 0570:2006 ) : cm<sup>3</sup>/cm<sup>2</sup>/s

#1	#2
BELOW 0.1	BELOW 0.1

NOTE) TEST AREA : 20 cm<sup>2</sup>  
 TEST PRESSURE : 100 Pa

(04) WATER REPELLENCY ( KS K 0590:2008, SPRAY TEST ) : RATING

#1	#2
5 5 5	5 5 5

(05) WATER RESISTANCE ( KS K ISO 811:2009, HYDROSTATIC PRESSURE TEST ) : cmH<sub>2</sub>O

#1	#2
ABOVE 1000	ABOVE 1000

NOTE) WATER PRESSURE : 60 cmH<sub>2</sub>O/min